



ScandCopyspeed SSP 754 K1

ScandCopyspeed is a flexible, light weight, self adhesive label paper which is specifically designed for A4 printer labels.

ScandCopyspeed is suitable for a variety of photocopier, laser and ink-jet printing systems. Good whiteness and brightness levels give aesthetically pleasing colour ink-jet prints as well as practical bar codes. The self adhesive laminate is produced to the optimum moisture content level required by laser and photocopier equipment manufacturers.

When pre-printing laminate intended for subsequent overprinting, care must be taken to control the laminate moisture and curl. Failure to do so can lead to feed and print problems particularly in laser and copier systems. Care also needs to be taken during storage and conversion.

We would advise that self adhesive laminates should be fed from the printer manufacturer's recommended input which, for desktop printers, is usually a multipurpose feed tray.

Face Material Properties

Basis weight	64 g/m ²	ISO 536
Caliper	82 microns	ISO 534
Smoothness (Bendtsen)	80 ml/min	

Adhesive

SSP 754 **Permanent**

ScandStick 754 is a high tack adhesive that performs well on a wide range of surfaces, including various boards.

754 gives very good adhesion to low energy surfaces such as polythene, both at room temperature and under chill conditions.

Suitable for use with ink-jet, laser and other variable information printable laminates, 754 has excellent resistance to edge bleed to prevent contamination inside printers.

It is recommended that products produced with 754 and destined for laser toner fusion work should be waste-trimmed on the edges.

Note: Not advised for labelling highly plasticised materials, eg: Flexible PVC.

Composition	rubber based hot melt
Minimum Application Temperature	0 °C
Service Temperature	-15 to +75 °C
Food contact	Meets composition requirement of indirect food additives regulation FDA 21-CRF 175-105

Backing

ScandSil Kraft 52 (K1) is a light weight kraft backing with good lay-flat properties.

Caliper	54 ±4 microns	ISO 534
Translucency	n/a	ISO 2469

Laminate

Laminate Shelf Life	12 months stored at 20°C/50% RH
Typical Laminate Caliper	155 ±15 microns

Food Packaging Applications: The adhesive raw materials are listed under European/US food packaging regulations (BgvV XIV or FDA 21 175.105) and are safe for use in limited contact with foodstuffs.

Toy and Packaging Regulations: The materials used have been tested and comply with the current heavy metals regulations EN71-3 Safety of Toys and the UK Packaging (Essential Requirements) Regulations 1998.

ScandCopyspeed SSP754 K1
Revision: 210811 - 106001L0N000

page 1 of 1
Replaces all previous information.

Self Adhesive Roll Products

ScandStick AB Box 25 S-263 21 Höganäs Sweden Tel +4642250050 Fax +4642250090 The values indicated in this leaflet are not intended to be a specification but a guide to the values that may generally be expected. Customers should independently determine, prior to use, the suitability of any material for a specific purpose. All information is subject to change without